

# ARCOL<sup>®</sup> POLYOL PPG 2000 - for special polyurethane applications

**General Properties and Applications** Arcol<sup>®</sup> Polyol PPG 2000 is a difunctional polyether polyol for the production of polyurethane products.

**Sampling** Moisture access should be prevented when taking product samples.

| Specification Property | Value       | Unit of measurement | Method        |
|------------------------|-------------|---------------------|---------------|
| Hydroxyl number        | 54.7 - 57.5 | mg KOH/g            | PET – 11 – 01 |
| Water content          | max. 0.050  | % by wt.            | PET – 19 – 01 |
| Acidity                | max. 0.020  | mg KOH/g            | PET – 01 – 01 |
| Viscosity at 25 °C     | 325 - 365   | mPa·s               | PET – 10 – 01 |

| Other Data* Property | Value        | Unit of measurement | Method    |
|----------------------|--------------|---------------------|-----------|
| Density at 20 °C     | approx. 1.01 | g/cm <sup>3</sup>   | DIN 51757 |

\* These values provide general information and are not part of the product specification

**Packaging** drums, IBCs, road tankers or tank containers

**Storage** Recommended storage temperature (°C): 20 – 40  
Shelf life (ex works): 12 months if stored in sealed containers

**Labeling and REACH applications** This product data sheet is only valid in conjunction with the latest edition of the corresponding Safety Data Sheet. Any updating of safety-relevant information – in accordance with statutory requirements – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. Information relating to the current classification and labeling, applications and processing methods and further data relevant to safety can be found in the currently valid Safety Data Sheet.



# ARCOL<sup>®</sup> POLYOL PPG 2000 - for special polyurethane applications

---

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

---

Editor: Business Unit Polyurethanes  
Bayer MaterialScience AG,  
D-51368 Leverkusen, Germany  
[www.bayermaterialscience.com](http://www.bayermaterialscience.com)

**Contact :**  
Michels, Erhard  
Tel. +49 214 / 30-81723