

ARCOL[®] Polyol 1108 - for flexible slabstock foams

General Properties and Applications

Arcol[®] Polyol 1108 is a low VOC (volatile organic compounds) inactive propylene oxide/ethylene oxide polyether triol. It is used extensively in conventional flexible polyether slabstock foams, either as the standard base polyol, or in combination with other polyols, to achieve particular effects and foam properties. It has been specifically designed for optimal secondary blowing agent compatibility with excellent physical properties of the resulting foams.

Sampling

Moisture access must be prevented when taking product samples.

Specification

| Property | Value | Unit of measurement | Method |
|-----------------|---------|---------------------|-----------|
| Hydroxyl number | 46 - 50 | mg KOH/g | PET-11-01 |
| Water content | ≤ 0.10 | % by wt. | PET-19-01 |
| Colour APHA | ≤ 40 | | PET-06-01 |
| Unsaturation | ≤ 50 | mEq/kg | PET-18-01 |

Other Data*

| Property | Value | Unit of measurement | Method |
|-----------------|---------------------------|---|-----------|
| Appearance | colourless to pale liquid | | PET-03-04 |
| Density 25 °C | 1.03 | g/cm ³ | DIN 51757 |
| Viscosity 25 °C | 595 - 755 | mPa·s | PET-10-01 |
| Flash point | > 165 | °C | DIN 51758 |
| TDI basic value | 7.4 | pbw Desmodur [®] T on 100 pbw Arcol [®] Polyol 1108 | |

* These values provide general information and are not part of the product specification

ARCOL[®] Polyol 1108 - for flexible slabstock foams

| | |
|--|---|
| Storage | <p>Recommended storage temperature (°C): 10 - 35</p> <p>Shelf life (ex works)</p> <p>12 months if stored in sealed, moisture-tight containers</p> <p>Partially used containers should be tightly resealed due to the hygroscopic nature of the product.</p> <p>Recommended temperature for processing (°C): 20 - 25.</p> |
| Labeling and REACH applications | <p>This product data sheet is only valid in conjunction with the latest edition of the corresponding Safety Data Sheet. Any updating of safety-relevant information – in accordance with statutory requirements – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. Information relating to the current classification and labeling, applications and processing methods and further data relevant to safety can be found in the currently valid Safety Data Sheet.</p> |
| Directions for Processing | <p>Arcol[®] Polyol 1108 can be processed into conventional polyurethane slabstock foams using regular formulations for standard polyols.</p> <p>Arcol[®] Polyol 1108 can be blended with other polyols including polymer polyols.</p> |

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

This product is not designated as „Medical Grade“* and therefore shall not be considered a candidate for the manufacture of a medical device or of intermediate products for medical devices, which are intended under normal use to be brought into direct contact with the patient's body (e.g., skin, body fluids or tissues, including indirect contact to blood)*. If the intended use of the product is for the manufacture of a medical device or of intermediate products for medical devices, Bayer MaterialScience AG must be contacted in advance to provide its agreement to sell such product for such purpose. Nonetheless, any determination as to whether a product is appropriate for use in a medical device or intermediate products for medical devices must be made solely by the purchaser of the product without relying upon any representations by Bayer MaterialScience AG. * Please see the "Guidance on Use of Bayer MaterialScience Products in a Medical Application" document. In case of questions, please contact: productsafety@bayerbms.com

Editor: Business Unit Polyurethanes
Bayer MaterialScience AG,
D-51368 Leverkusen, Germany
www.bayermaterialscience.com

Contact :
Business Unit Polyurethanes
e-mail: pur@bayer.com

page 2 of 2

Edition 2009-12-07

Replaces edition dated 2007-03-12

Product Datasheet