

Polyethylene HE1878

High Density Polyethylene for Crosslinked Pipes (PE-X)

Description

HE1878 is a high molecular weight, high density polyethylene specially designed for production of crosslinked pipes (PE-X)

Applications

HE1878 is recommended for the production of crosslinked pipes used in

Plumbing
Domestic water
Domestic gas
District heating

Relining
Industrial applications
Heating

Specifications

HE1878 is intended to fulfill following standards and regulations, in case of appropriate industrial manufacturing standard procedures applied and a continuous quality system is implemented.

DIN 16892
DIN 16893

EN ISO 15875
ASTM F 876

Special features

HE1878 is a free flowing powder for the PE-Xa, peroxide crosslinking process. The material is only stabilized for transporting and storage. Crosslinking agent (e.g. peroxide) and stabilisers have to be added by the pipe manufacturer. Good crosslink response and well-balanced powder size distribution enable effective soaking and a stable pipe production.

Economical pipe production
Cleanliness

Enhanced processability
Excellent product consistency

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (Base Resin)	955 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/21,6 kg)	3 g/10min	ISO 1133
Tensile Strain at Break	> 600 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	22 MPa	ISO 527-2

Processing Techniques

The actual conditions will depend on the type of equipment used.

Extrusion

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polyethylene HE1878

The actual extrusion conditions will depend on the type of equipment used. They will also depend on size and wall thickness of the pipe produced.

HE1878 is successfully used in the industry on the older RAM (Engel) process as well as on the newer type of screw extrusion equipment in combination with different PE-Xa crosslinking methods.

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borealis representative for such particulars.

Storage

HE1878 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Recycling

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the products.

Recovery and disposal of polyolefins
Information on emissions from processing and fires
"Safety data sheet" / "Product safety information sheet"
Statement on compliance to food contact regulations
Statement on compliance to regulations for drinking water pipes



Polyethylene
HE1878

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.